

## American Cherry Lumber

### DISTRIBUTION

Throughout Midwestern and Eastern U.S. Main commercial areas: Pennsylvania, Virginia, West Virginia, and New York.

### GENERAL DESCRIPTION

The heartwood of cherry varies from rich red to reddish brown and will darken with age and on exposure to light. In contrast, the sapwood is creamy white. The wood has a straight-grain, a fine, uniform, satiny and smooth texture, and naturally may contain brown pith flecks and small gum pockets.

### WORKING PROPERTIES

Cherry is easy to machine, nails and glues well, and when sanded and stained, it produces an excellent, smooth finish. It dries fairly quickly with moderately high shrinkage, but dimensionally is stable after kiln-drying.





















### PHYSICAL PROPERTIES

Cherry is of medium density with good bending properties, has low stiffness, and medium strength and shock resistance. **AVAILABILITY** Readily available.

### MAIN USES

Fine furniture and cabinet making, moulding and millwork, kitchen cabinets, paneling, flooring, doors, boat interiors, musical instruments, turnings, and carvings.



MACHINING				
NAILING				
SCREWING				
GLUING				
FINISHING				

Call us today for all of your lumber needs!

<b>AETNA PLYWOOD, INC. CORPORATE</b> 1401 St. Charles Road Maywood, IL 60153 PH: 708.343.1515 Fax: 708.343.1616	<b>AETNA PLYWOOD, INC. ROCKFORD</b> 2112 12th Street Rockford, IL 61104 PH: 815.968.0921 Fax: 815.968.4720	<b>AETNA PLYWOOD, INC. INDIANAPOLIS</b> 6350 Brookville Road Indianapolis, IN 46219 PH: 317.353.6281 Fax: 317.356.3503	<b>AETNA PLYWOOD, INC. MINNESOTA</b> 4250 Otter Lake Road White Bear Lake, MN 55110 PH: 651.407.2800 Fax: 651.407.2801	<b>HORN LUMBER CICERO</b> 4700 W 19th Street Cicero, IL 60804 PH: 773.847.7397 Fax: 773.847.7798
---	--	--	--	--