

Walnut Lumber

DISTRIBUTION

Throughout Eastern U.S. Principal commercial region is the Central states.

GENERAL DESCRIPTION

The sapwood is creamy white, while the heartwood is light brown to dark chocolate brown, occasionally with a purplish cast and darker streaks. It is usually supplied steamed, to darken the sapwood. The wood is generally straight-grained; sometimes with wavy or curly grain that produces an attractive and decorative figure.

WORKING PROPERTIES

It works easily with hand and machine tools, and nails, screws, and glues well. It holds paint and stain very well for an exceptional finish and is readily polished. It dries slowly, and care is needed to avoid kiln degrade. It has good dimensional stability.

PHYSICAL PROPERTIES


Walnut is a tough hardwood of medium density, with moderate bending and crushing strengths, and low stiffness. It has a good steam-bending classification.

AVAILABILITY

Reasonable availability.

MAIN USES

Furniture, cabinets, architectural millwork, doors, flooring, paneling, and gun stocks. It is a favored wood for use in contrast with lighter-colored species.



Call us today for this and other lumber!

AETNA PLYWOOD, INC. CORPORATE 1401 St. Charles Road Maywood, IL 60153 PH: 708.343.1515 Fax: 708.343.1616	AETNA PLYWOOD, INC. ROCKFORD 2112 12th Street Rockford, IL 61104 PH: 815.968.0921 Fax: 815.968.4720	AETNA PLYWOOD, INC. INDIANAPOLIS 6350 Brookville Road Indianapolis, IN 46219 PH: 317.353.6281 Fax: 317.356.3503	AETNA PLYWOOD, INC. MINNESOTA 4250 Otter Lake Road White Bear Lake, MN 55110 PH: 651.407.2800 Fax: 651.407.2801	HORN LUMBER CICERO 4700 W 19th Street Cicero, IL 60804 PH: 773.847.7397 Fax: 773.847.7798
---	--	--	--	--